

AMENDMENTS TO THE CLAIMS

Claim 1 (currently amended): A porous insulating film consisting essentially of a highly heat resistant polyimide resin film having a fine porous structure wherein:

a) fine continuous channels reaching to both surfaces of the film in a nonlinear fashion have a mean pore size of ~~0.04~~ 0.05 – 5 μm in the center and both surfaces of the film and a porosity of 15 – 80%; and

b) the polyimide resin film consists essentially of a polyimide obtained from the combination of at least one tetracarboxylic acid component and a diamine component - ; and

c) the film has a thickness of 5 – 150 μm and a resistance to passage of air of from 30 sec/100 cc to 2000 sec/100 cc.

Claim 2 (original): A porous insulating film according to claim 1, wherein the mean pore size is 0.05–1 μm .

Claim 3 (original): A porous insulating film according to claim 1, wherein the porosity is 30-80%.

Claim 4 (original): A porous insulating film according to claim 1, which has a thickness of 5-150 μm .

Claim 5 (previously canceled).

5

Claim ~~6~~ (original): A porous insulating film according to claim 1, which is fabricated by a film casting method.

6

Claim ~~7~~ (original): A porous insulating film according to claim 1, wherein the dielectric constant is no greater than 2.5.

Claims 8-9 (previously canceled).

⁸
Claim ~~10~~ (currently amended): A porous insulating film consisting essentially of a highly heat resistant polyimide resin film having a fine porous structure wherein:
a) fine continuous channels reaching to both surfaces of the film in a nonlinear fashion have a mean pore size of 0.01 ± 0.05 - 5 μm in the center and both surfaces of the film; and
b) the polyimide resin film consists essentially of a polyimide obtained from the combination of at least one tetracarboxylic acid component and a diamine component and has
(i) a thickness of 5 - 100 μm ,
(ii) a resistance to passage of air of from 30 sec/100 cc to 2000 sec/100 cc,
(iii) a heat resistance temperature of at least 200°C and
(iv) a heat shrinkage of greater than $\pm 1\%$ at 105°C.

Claim 11 (previously canceled).

Claims 12-14 (canceled).

⁹
Claim ~~13~~ (previously added): A battery separator comprising a porous insulating film according to claim 10.

¹⁰
Claim ~~16~~ (previously added): A porous insulating film according to claim 1 or ~~10~~,⁸ wherein the tetracarboxylic acid component is selected from a biphenyltetracarboxylic dianhydride, pyromellitic dianhydride and a benzophenonetetracarboxylic dianhydride.

¹²
Claim ~~17~~ (previously added): A porous insulating film according to claim 1 or ~~10~~,⁸ wherein the diamine component is selected from a phenylenediamine or a diaminodiphenylether.

⁷
Claim ~~18~~ (previously added): A porous insulating film according to claim 1, wherein the pores in the porous structure are arranged in the film substantially parallel to the film surfaces.

11
10
Claim ~~19~~ (previously added): A porous insulating film according to claim ~~16~~, wherein the biphenyltetracarboxylic dianhydride is 3,3',4,4'-biphenyltetracarboxylic dianhydride.

13
8
Claim ~~20~~ (previously added): A porous insulating film according to claim ~~10~~, wherein the pores in the porous structure are arranged in the film substantially parallel to the film surfaces.